

Multi layer Sun Selector

Type: **SUNSAVER DIFF 75%/ C721**

Film usage	:	Greenhouse cover
Width	:	Up to 15 meters
Thickness	:	180 micron
Length	:	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	23.0
	TD	“	MPa	22.0
Elongation at break	MD	“	%	650
	TD	“	%	750
Tear resistance	MD	ASTM D1922	Gr./mm.	8500
	TD	“	Gr./mm	12000
Falling dart drop impact		ASTM D-1709	Gr.	1000

Light transmission in PAR	%	ASTM D-1003	87
Diffused light tr .in PAR	%	"	75
Thermicity 7 – 15 micron	%	"	90
Anti Drip		Yes (place in accordance to instruction)	
			Typical values